

LGC MED / BDC

Park, Han Sol

<u>Approved</u>

LGC MED / BDC Ahn, Soon Ho

PRODUCT SPECIFICATION CONFIDENTIAL TENTATIVE Document No.

BCY-PS-MG1-Rev0

2012-05-11

Rev 0

Description

Lithium Ion 18650 MG1 2900mAh

PRODUCT SPECIFICATION-TENTATIVE

Rechargeable Lithium Ion Battery Model: 18650 MG1 2900mAh



20 YOIDO-DONG YOUNGDUNGPO-GU, **SEOUL 150-721, KOREA**

TEL: (82) 2-3773-1114 FAX: (82) 2-3773-7005

http://www.lgchem.com



PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

Document No.
BCY-PS-MG1-Rev0

Date 2012-05-11

<u>Rev</u>

Revision History

| Revision | Date | Originator | Description |
|----------|------------|---------------|------------------|
| 0 | 2012-05-11 | Park, Han Sol | Original Release |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

Lithium Ion 18650 MG1 2900mAh

PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

Document No.

<u>Date</u>

<u>Rev</u>

BCY-PS-MG1-Rev0

2012-05-11

Contents

<u>Description</u>

| Revision History |
|---|
| Contents |
| 1. General Information |
| 1.1 Scope |
| 1.2 Application |
| 1.3 Product Classification |
| 1.4 Model Name |
| 2. Nominal Specification |
| 2.1 Capacity |
| 2.2 Nominal Voltage |
| 2.3 Standard Charge |
| 2.4 Max. Charge Voltage |
| 2.5 Max. Charge Current |
| 2.6 Standard Discharge |
| 2.7 Max. Discharge Current |
| 2.8 Weight |
| 2.9 Operating Temperature |
| 2.10 Storage Temperature (for shipping state) |
| 3. Appearance and Dimension |
| 3.1 Appearance |
| 3.2 Dimension |
| 4. Performance Specification |
| 4.1 Standard Test Condition |
| 4.2 Electrical Specification |
| 4.3 Environmental Specification |
| 4.4 Mechanical Specification |
| 4.5 Safety Specification |
| 5. Cautions and Prohibitions in Handling |

Lithium Ion 18650 MG1 2900mAh

PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

Document No. BCY-PS-MG1-Rev0

2012-05-11

<u>Rev</u>

1. General Information

1.1 Scope

Description

This product specification defines the requirements of the rechargeable lithium ion battery to be supplied to the Customer by LG Chem.

1.2 Application: Light Electric Vehicle

1.3 Product classification: Cylindrical rechargeable lithium ion battery

1.4 Model name: 18650 MG1

2. Nominal Specification

| Item | Condition / Note | Specification | |
|---|----------------------------|---------------------------------------|--|
| 2.1 Capacity | Std. charge / discharge | Nominal 2,850 mAh (C _{nom}) | |
| 2.1 Supusity | (Refer to 4.1.1./ 4.1.2) | Minimum 2,750 mAh (C _{min}) | |
| 2.2 Nominal Voltage | Average for Std. discharge | 3.62V | |
| | Constant current | 0.5C (1,425mA) | |
| 2.3 Standard Charge (Refer to 4.1.1) | Constant voltage | 4.2V | |
| , | End condition(Cut off) | 50mA | |
| 2.4 Max. Charge Voltage | | 4.2V | |
| 2.5 Max. Charge Current | | 1.0C(2,850mA) | |
| 2.6 Standard Discharge | Constant current | 0.2C (570mA) | |
| (Refer to 4.1.2) | End voltage(Cut off) | 2.5V | |
| 2.7 Max. Discharge Current | | 10A | |
| 2.8 Weight | Approx. | 46.0 g | |
| 2.0 Operating Temperature | Charge | 0 ~ 45℃ | |
| 2.9 Operating Temperature | Discharge | -20 ~ 60℃ | |
| | 1 month | -20 ~ 60 ℃ | |
| 2.10 Storage Temperature (for shipping state) | 3 month | -20 ~ 45℃ | |
| | 1 year | -20 ~ 20℃ | |

^{*} Shipping state : About 40% capacity of fully charged state

PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

Document No. BCY-PS-MG1-Rev0

2012-05-11

<u>Rev</u>

<u>Description</u> Lithium Ion 18650 MG1 2900mAh

3. Appearance and Dimension

3.1 Appearance


There shall be no such defects as deep scratch, crack, rust, discoloration or leakage, which may adversely affect the commercial value of the cell.

3.2 Dimension

Diameter : 18.3 + 0.1/-0.3 mm (Max. 18.4 mm)

Diameter is defined as the largest data value measured on the "A" area of a cylindrical cell.

Height : $65.0 \pm 0.2 \text{ mm}$ (Max. 65.2 mm)



4. Performance Specification

4.1 Standard test condition

4.1.1 Standard Charge

Unless otherwise specified, "Standard Charge" shall consist of charging at constant current of 1,425mA. The cell shall then be charged at constant voltage of 4.2V while tapering the charge current. Charging shall be terminated when the charging current has tapered to 50mA. For test purposes, charging shall be performed at 25° C \pm 2° C.

4.1.2 Standard Discharge

"Standard Discharge" shall consist of discharging at a constant current of 570mA to 2.5V. Discharging is to be performed at 25 $^{\circ}$ C \pm 2 $^{\circ}$ C unless otherwise noted (such as capacity versus temperature).

4.1.3 High Drain rate Charge/discharge condition

Cells shall be charged at constant current of 1,000mA to 4.2V with end current of 100mA. Cells shall be discharged at constant current of 6,000mA to 2.75V. Cells are to rest 5 minutes after charge and 5 minutes after discharge.

Lithium Ion 18650 MG1 2900mAh

PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

Document No. BCY-PS-MG1-Rev0

2012-05-11

Rev 0

4.2 Electrical Specification

Description

| Item | Condition | Specification |
|----------------------|---|---|
| 4.2.1 | Cell shall be measured at 1kHz after charge per | \leq 35 m Ω , without PTC |
| Initial AC Impedance | 4.1.1. | |
| 4.2.2 | Cells shall be charged per 4.1.1 and discharged | $C_{ini} \geq 2,750 \text{ mAh } (C_{min})$ |
| Initial Capacity | per 4.1.2 within 1h after full charge. | |
| 4.2.3 | Cells shall be charged and discharged per | \geq 70 % (of C _{min} in 2.1) |
| Cycle Life | 4.1.3, 500 cycles. A cycle is defined as one | |
| | charge and one discharge. 501st discharge | |
| | capacity shall be measured per 4.1.1 and 4.1.2 | |

4.3 Environmental specification.

| Item | Condition | Specification |
|-------------------------|---|---------------------------------|
| 4.3.1 | Cells shall be charged per 4.1.1 and stored in a | Capacity remaining rate |
| Storage Characteristics | temperature-controlled environment at 25°C ± | ≥ 90% (C _{ini} in 2.1) |
| | 2°C for 30 days. After storage, cells shall be | |
| | discharged per 4.1.2 to obtain the remaining | |
| | capacity.* | |
| 4.3.2 | Cells shall be charged per 4.1.1 and stored in a | No leakage, |
| High Temperature | temperature-controlled environment at 60°C for | Capacity recovery rate ≥ |
| Storage Test | 1 week. After storage, cells shall be discharged | 80% |
| | per 4.1.2 and cycled per 4.1.1 and 4.1.2 for 3 | |
| | cycles to obtain recovered capacity*. | |
| 4.3.3 | Cells are charged per 4.1.1 and stored at 60°C | No leakage, No rust |
| High Temperature and | (95% RH) for 168 hours. After test, cells are | Capacity recovery rate ≥ |
| High Humidity Test | discharged per 4.1.2 and cycled per 4.1.1 and | 80% |
| | 4.1.2 for 3 cycles to obtain recovered capacity. | |
| 4.3.4 | 65°C (8h) \leftarrow 3hrs \rightarrow -20°C (8h) for 8 cycles | No leakage |
| Thermal Shock Test | with cells charged per 4.1.1 After test, cells are | Capacity recovery rate ≥ |
| | discharged per 4.1.2 and cycled per 4.1.1 and | 80% |
| | 4.1.2 for 3 cycles to obtain recovered capacity. | |

^{*} Remaining Capacity: After storage, cells shall be discharged with Std. condition(4.1.2) to measure the remaining capacity.

** Recovery Capacity: After storage, cells shall be discharged with Std condition(4.1.2), and then cells shall be charged with std. charge condition(4.1.1), and then discharged with Std. condition(4.1.2). This charge / discharge cycle shall be repeated three times to measure the recovery capacity.

PRODUCT SPECIFICATION



Lithium Ion 18650 MG1 2900mAh

Document No. BCY-PS-MG1-Rev0 Date 2012-05-11

<u>Rev</u>

| 4.3.5 Temperature Dependency of | | per 4.1.1 at 25°C ± 2°C 4.1.2 at the following | |
|---------------------------------|-------------|---|--------------------------|
| Capacity | Charge | Discharge | Capacity |
| | | -10℃ | 70% of C _{ini} |
| | 25 ℃ | 0℃ | 80% of C _{ini} |
| | 25 0 | 23℃ | 100% of C _{ini} |
| | | 60℃ | 95% of C _{ini} |

4.4 Mechanical Specification

| Item | Condition | Specification |
|----------------|---|-----------------------|
| 4.4.1 | Cells charged per 4.1.1 are dropped onto an oak board | No leakage |
| Drop Test | from 1 meter height for 1 cycle, 2 drops from each cell | No temperature rising |
| | terminal and 1 drop from side of cell. (Total number of | |
| | drops =3). | |
| 4.4.2 | Cells charged per 4.1.1 are vibrated for 90 minutes per | No leakage |
| Vibration Test | each of the three mutually perpendicular axes (x, y, z) | |
| | with total excursion of 0.8mm, frequency of 10Hz to | |
| | 55Hz and sweep of 1Hz change per minute. | |

4.5 Safety Specification

| Item | Condition | Specification |
|------------------|--|---------------------|
| | Cells are discharged per 4.1.2, then charged at constant | |
| 4.5.1 | current of 3 times the max. charge condition and | No ovalado. No firo |
| Overcharge Test | constant voltage of 4.2V while tapering the charge | No explode, No fire |
| | current. Charging is continued for 7 hours (Per UL1642). | |
| 4.5.2 | Cells are charged per 4.1.1, and the positive and | |
| External Short - | negative terminal is connected by a $100m\Omega$ -wire for 1 | No explode, No fire |
| Circuiting Test | hour (Per UL1642). | |
| 4,5.3 | Calle are discharged at constant ourself of 0.00 to | |
| Overdischarge | Cells are discharged at constant current of 0.2C to | No explode, No fire |
| Test | 250% of the minimum capacity. | |

Lithium Ion 18650 MG1 2900mAh

Description

PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

Document No. BCY-PS-MG1-Rev0

2012-05-11

<u>Rev</u>

| 4.5.4 Heating Test | Cells are charged per 4.1.1 and heated in a circulating air oven at a rate of 5°C per minute to 130°C. At 130°C, oven is to remain for 10 minutes before test is discontinued (Per UL1642). | No explode, No fire |
|-----------------------|---|---------------------|
| | , | |
| | Cells charged per 4.1.1 are impacted with their | |
| 4.5.5 | longitudinal axis parallel to the flat surface and | No ovolodo. No firo |
| Impact Test | perpendicular to the longitudinal axis of the 15.8mm | No explode, No fire |
| | diameter bar (Per UL1642). | |
| 4.5.7 | Cells charged per 4.1.1 are crushed with their | |
| 4.5.7 | longitudinal axis parallel to the flat surface of the | No explode, No fire |
| Crush Test | crushing apparatus (Per UL1642). | |

5. Caution and Prohibition in Handling

Warning for using the lithium ion rechargeable battery. Mishandling of the battery may cause heat, fire and deterioration in performance. Be sure to observe the following.

Caution

- When using the application equipped with the battery, refer to the user's manual before usage.
- Please read the specific charger manual before charging.
- Charge time should not be longer than specified in the manual.
- When the cell is not charged after long exposure to the charger, discontinue charging.
- Battery must be charged at operating temperature range 0 ~ 45 ℃.
- Battery must be discharged at operating temperature range -20 ~ 60 ℃.
- Please check the positive(+) and negative(-) direction before packing.
- When a lead plate or wire is connected to the cell for packing, check out insulation not to short-circuit.
- Battery must be stored separately.
- Battery must be stored in a dry area with low temperature for long-term storage.
- Do not place the battery in direct sunlight or heat.
- Do not use the battery in high static energy environment where the protection device can be damaged.
- When rust or smell is detected on first use, please return the product to the seller immediately.
- The battery must be away from children or pets
- When cell life span shortens after long usage, please exchange to new cells.



PRODUCT SPECIFICATION

CONFIDENTIAL TENTATIVE

BCY-PS-MG1-Rev0

2012-05-11

<u>Rev</u>

Prohibitions

- Do not use different charger. Do not use cigarette jacks (in cars) for charging.
- Do not charge with constant current more than maximum charge current.
- Do not disassemble or reconstruct the battery.
- Do not throw or cause impact.
- Do not pierce a hole in the battery with sharp things. (such as nail, knife, pencil, drill)
- Do not use with other batteries or cells.
- Do not solder on battery directly.
- Do not press the battery with overload in manufacturing process, especially ultrasonic welding.
- Do not use old and new cells together for packing.
- Do not expose the battery to high heat. (such as fire)
- Do not put the battery into a microwave or high pressure container.
- Do not use the battery reversed.
- Do not connect positive(+) and negative(-) with conductive materials (such as metal, wire)
- Do not allow the battery to be immerged in or wetted with water or sea-water.